The study of 3-strand PP/PE composite monofilament Rope

Jian-gao Shi^{1*}, Wenwen Yu¹, Yongli Liu¹, Lei Wang¹, Xiaoxue Chen¹, Luming

 $Wang^1$ and Wen-zhu Zhong²

¹East China Sea Fisheries Research Institute, Chinese Academy of Fishery Sciences, Shanghai, China

²Fishery Machinery and Instrument Research Institute, Chinese Academy of Fishery Sciences, Shanghai, China

^{*}jiangaoshi666@163.com

Keywords: PP/PE composite monofilament rope; tensile mechanical properties; safety **Abstract.** Performance-price ratio, safety and tensile mechanical properties of the new 3-strand fishing PP/PE composite monofilament rope ("PP/PE composite monofilament rope") were studied in this paper. PP/PE composite monofilament rope was made with the fishing polypropylene/Polyethylene (PP/PE) composite monofilament using modification technology. The result shows linear density, breaking load, breaking strength and percentage of breaking elongation of PP/PE composite monofilament rope in the diameter of 8.0mm are respectively 32ktex, 9.77kN, 3.05cN/dtex and 18%; if common fiber rope is replaced by PP/PE composite monofilament rope without modifying the rope, not only the rope linear, density diameter, but also the netting gear resistance and raw material consumption can be reduced; with safety and tensile mechanical properties, there is an extensive prospect of industrialized application for PP/PE composite monofilament rope.

Introduction

PP rope and PE rope are widely used in trawl fisheries, deep water cage farming and barrier net farming, they are made of common PE monofilament and common PP monofilament in a single rope process, and their tensile mechanical properties need to be improved; as the basic structural element of a rope, the common PE monofilament and common PP monofilament are respectively made of high density PE (HDPE) and PP in the traditional spinning process ^[1-8]. The rope performance directly determines the expansion, complication, offshore work specialization and anti-wave safety of marine fisheries and projects(e.g. trawl, deep water cage, large floating rope barrier net, and barrier net dam for ecological marine farming, etc) ^[9-12]. The progress of modern fishery brings a higher demand for the performance-price ratio, safety and tensile mechanical properties of the rope, and it urgently needs to carry out the research, development and industrialized application of new rope materials ^[7-18]. The ultra high molecular weight polyethylene fiber rope has outstanding properties but is expensive at present, and there are only a few researches on its application and demonstration in fisheries of China, so it can not be widely generalized ^[5, 9-20]. High performance but low price ropes are greatly demanded in the modern fisheries, so some new materials of modified fiber and reinforced fiber in a high performance-price ratio are chosen ^{[1-8,} ^{11-12]}. Technological progress of fiber materials (such as nano-modification and modification, etc) realizes the research, development and industrialized application of new materials for high

performance ropes in fisheries, and has made some critical achievements ^[1-8, 11-12]. In this paper, the test result of PP/PE composite monofilament ropes carried out in the East China Sea Fisheries Research Institute during 2012~2015 was taken as a basis to compare and analyze the performance-price ratio, safety and tensile mechanical properties between the PP/PE composite monofilament rope and the common fiber rope, expecting to provide basic data for the rope production, structural optimization and related fishery design.

Experimental

Material preparation

Preparation of fishing PP/PE composite monofilament

Screened spinning dry HDPE resin, PP resin and white oil auxiliary agent are mixed to prepare four types of PP/PE composite monofilaments (Table 1) in different PP mass percentages using modification and a special spinning process (drawing ratio 8.3~8.4), and the PP/PE composite monofilament with the highest breaking strength therein is used as the new basal fiber material for PP/PE composite monofilament rope, i.e. the fishing PP/PE composite monofilament.

SN	PP mass percentage (%)	Linear density (dtex)	Breaking strength (cN/dtex)	Knot breaking strength (cN/dtex)	Percentage of breaking elongation (%)	Drawing ratio
1	41~43	4.25	6.13	5.98	15.0	8.4
2	80~84	4.24	6.54	6.33	12.5	8.4
3	120~124	4.03	6.47	5.38	12.0	8.3
4	398~402	5.06	5.64	4.78	11.8	8.3

Table 1 Impact of PP mass percentage on the mechanical properties of PP/PE composite monofilament

Preparation of PP/PE composite monofilament rope

The PP/PE composite monofilament rope in a diameter of 8.0mm is made of the basal fiber of fishing PP/PE composite monofilament via ring twisting, strand combining, and rope making, checking and post-treating. The common 3-strand polyamide (PA) rope, common 3-strand PE rope an 4-strand twisted PE rope are made of the common synthesized fiber as per the indexes for the standard acceptable product ^[1-2, 12, 21].

Testing method

Test instruments cover an electronic balance FA2004N, an electronic scale ACS-15A from China, a strength tester INSTRON-4466 (range 10kN, resolution 0.1N) from Britain and a strength tester RHZ-1600 (range 1600kN, resolution 0.08kN) from Germany.

The test was carried out in a standard lab at $(20\pm3)^{\circ}$ C and RH $(65\pm5)\%$ constantly, and samples were balanced in the lab for 24h above. The tensile mechanical properties of PP/PE composite monofilament were tested by the strength tester INSTRON-4466 at a drawing speed of 300mm/min and a sample length of 750mm. The tensile mechanical properties of PP/PE composite monofilament rope were tested by the strength tester RHZ-1600 at a drawing speed of 270mm/min. The tensile mechanical properties of PP/PE composite monofilament were tested according to SC/T 5005^[22]. The tensile mechanical properties of PP/PE composite monofilament rope were tested according to GB/T 8834^[23]. Valid data obtained in the test were managed according to data processing specification of the corresponding standard^[21-23].

Results and analysis

Analysis for tensile mechanical properties of fishing PP/PE composite monofilament

Table 1 shows the tensile mechanical properties of four types of PP/PE composite monofilament in different PP mass percentages. According to Table 1, the PP/PE resin mixture with a PP mass percentage of 80%~84% is the optimal as the PP/PE composite monofilament is given the highest breaking strength ("fishing PP/PE composite monofilament" differing from the other three types of PP/PE composite monofilament in Table 1), and it is used as the new basal fiber for making the PP/PE composite monofilament rope. The breaking strength, knot breaking strength and percentage of breaking elongation of the fishing PP/PE composite monofilament are respectively 65.4cN/tex, 63.3cN/tex and 12.5%, in which, the breaking strength and knot breaking strength are improved by 25.8% and 75.8% than the fishing PE monofilament are modified by the modification, the molecular chain is gradually arranged more closely along the drawing direction with the enhanced orientation, and thus the crystallinity, orientation, breaking strength and knot breaking strength of the fishing PP/PE composite monofilament are increased ^[1-8]. Table 2 shows the comparison of tensile mechanical properties between the fishing PP/PE composite monofilament and common synthesized fibers.

Fiber type	Linear density (dtex)	Breaking strength (cN/dtex)	Percentage of breaking elongation (%)		
Fishing PP/PE composite	424	6.54	12.5		
monofilament					
Common PA fiber ^{*1}	230	5.50	22.0		
Common PE monofilament ^{*2}	360	5.20	20.0		
Note: *1 The common PA fiber is bought from the market; *2 The common PE monofilament					
conforms to the current standard.					

 Table 2 Comparison of tensile mechanical properties between fishing PP/PE composite monofilament and common fibers

The high breaking strength is an important property of the fishing PP/PE composite monofilament. Table 2 shows the fishing PP/PE composite monofilament has a distinctly superior breaking strength than common synthesized fibers and its strength is 18.9% and 25.8% higher than the common PA fiber and the common PE fiber respectively. Extensibility is a key factor in the material characteristics and the application properties, and low percentage of breaking elongation is another important property of the fishing PP/PE composite monofilament; comparing with common PE monofilament, the high molecular chain of fishing PP/PE composite monofilament has a low elongation deformation rate in drawing (being elongated or drifted), and the percentage of breaking elongation of fishing PP/PE composite monofilament is 12.5%, 43.2% and 37.5% lower than the common PA fiber and the common filament.

Analysis for tensile mechanical properties of fishing PP/PE composite monofilament rope

The PP/PE composite monofilament rope in a diameter of 8.0mm is made of the fishing PP/PE composite monofilament, and the test result of its tensile mechanical properties and the comparison

with common synthesized bier ropes are shown in Table 3.

common synthetic fiber ropes									
Rope	Diameter	Linear density	Breaking strength	Breaking strength	Percentage of breaking elongation				
	(mm)	(ktex)	(k N)	(cN/dtex)	(%)				
PP/PE composite monofilament rope	8.0	32.0	9.77	3.05	18				
Acceptable product of 3-strand PA rope ^[1, 21]	8.0	40.0	9.00	2.25	55~63				
Acceptable product of 3-strand PE monofilament rope ^[1, 21]	8.0	32.7	5.85	1.79	45~55				
4-strand twisted PE rope ^[1, 24]	8.0	32.1	6.28	1.96	45~55				
4-strand twisted PE rope ^[1, 24]	9.0	40.6	7.92	1.95	45~55				
Acceptable product of 3-strand PE monofilament rope ^[1,21]	10	49.0	8.85	1.81	45~55				

 Table 3 Comparison of tensile mechanical properties between PP/PE composite ropes and common synthetic fiber ropes

Analysis for the breaking strength and energy saving and consumption reducing effect of PP/PE composite monofilament rope

The rope breaking strength is mainly determined by the basal fiber material, rope yarn strength load utilization rate and rope making process (e.g. rope yarn twist, rope yarn arrangement, rope length of lay and number of rope strands), etc ^[1-2, 9-20]. Table 3 shows that the PP/PE composite monofilament rope has a superior breaking strength than common fiber ropes, and the 3-strand PA rope in a diameter of 8.0mm is replaced by the PP/PE composite monofilament rope in the same diameter for the fishing rope, the rope breaking load is improved by 8.6%, the linear density is reduced by 20%, the raw material consumption is reduced by 20%, and the fishing rope cost is cut off correspondingly; when the 3-strand PE monofilament rope in a diameter of 8.0mm is replaced by the PP/PE composite monofilament rope in the same diameter for the fishing rope, the rope breaking load is improved by 67.0%, the linear density is reduced by 2.1%, and the raw material consumption is reduced by 2.1%; when the 4-strand twisted PE monofilament rope in a diameter of 9.0mm is replaced by the PP/PE composite monofilament rope in a diameter of 8.0mm for the fishing rope, the rope breaking load is improved by 23.4%, the linear density is reduced by 21.2%, the rope diameter is reduced by 11.1%, the raw material consumption is reduced by 21.2%, and the netting gear resistance in water is reduced correspondingly; when the 3-strand PE monofilament rope in a diameter of 10.0mm is replaced by the PP/PE composite monofilament rope in a diameter of 8.0mm for the fishing rope, the rope breaking load is improved by 10.4%, the linear density is reduced by 34.7%, the rope diameter is reduced by 20%, the raw material consumption is reduced by 34.7%, and the netting gear resistance in water is reduced correspondingly. In all, comparing with common fiber ropes, the PP/PE composite monofilament rope has a superior breaking load with distinctly reduced consumption and resistance; in fisheries production, the 3-strand PA rope in a diameter of 8.0mm, the 4-strand twisted PE rope in a diameter of 9.0mm, and the 3-strand PE

monofilament rope in a diameter of 10mm can be replaced by the PP/PE composite monofilament rope in the same diameter to reduce the netting gear resistance in water, improve the netting gear safety, reduce the rope linear density and raw material consumption, and promote the energy saving and consumption reducing without modifying the advantage of breaking load.

Analysis for the breaking strength and breaking elongation of PP/PE composite monofilament rope Table 3 shows that the PP/PE composite monofilament rope has higher breaking strength and lower percentage of breaking elongation than common fiber ropes. The breaking strength of PP/PE composite monofilament rope in a diameter of 8.0mm is improved by 35.6%, 70.4%, 55.6%, 56.4% and 68.5% than the 3-strand PA rope in diameter of 8.0mm, 3-strand PE monofilament rope in a diameter of 8.0mm, 4-strand twisted PE rope in a diameter of 8.0mm, 4-strand twisted PE rope in a diameter of 9.0mm and 3-strand PE monofilament rope in a diameter of 10mm respectively; the percentage of breaking elongation is reduced by 69.5%, 64.0%, 64.0%, 64.0% and 64.0% than the 3-strand PA rope in diameter of 8.0mm, 3-strand PE monofilament rope in a diameter of 8.0mm, 4-strand twisted PE rope in a diameter of 8.0mm, 4-strand twisted PE rope in a diameter of 9.0mm and 3-strand PE monofilament rope in a diameter of 10mm respectively. The distinct differences of breaking strength and elongation between the PP/PE composite monofilament rope and common fiber ropes are mainly caused by the different tensile mechanical properties of the basal fibers. The PP/PE composite monofilament rope is made of the basal fiber of fishing PP/PE composite monofilament with a breaking strength of 6.52cN/dtex and an percentage of breaking elongation of 12.5% while the 3-strand PA rope is made of common PA fiber with a breaking strength of 5.50cN/dtex and an percentage of breaking elongation of 22.0%, the breaking strength of common PE monofilament is 5.20cN/dtex and the breaking elongation is 20.2% (Table 2), so there is a distinct difference of tensile mechanical properties between the fishing PP/PE composite monofilament and common synthesized fibers. High breaking strength and low elongation are important features for the fishing PP/PE composite monofilament differing from common synthesized fibers. The internal molecular structure of the fishing PP/PE composite monofilament is modified by the cross-link modifying technology, the molecular chain is arranged more closely, and the chain stretch is inhibited, so this fishing PP/PE composite monofilament in a specific aggregative structure is given a higher breaking strength and a low elongation, and the PP/PE composite monofilament rope twisted by it has a higher breaking strength and a lower elongation than common fiber ropes (Table 3) ^[1-2, 9-20]. Comparing with the fishing PP/PE composite monofilament, the molecular interacting forces of common synthesized fibers in Table 2 are small, and the elongation strains are large, so the common fiber ropes are shaped with low breaking strengths and larger elongations (Table 3)^[1-8].

Analysis for the safety of PP/PE composite monofilament rope

Comparing with common fiber ropes (e.g. 3-strand PA rope, 3-strand PE monofilament rope and 4-strand twisted PE rope) in diameters of 8.0mm~10mm in Table 3, the breaking load of PP/PE composite monofilament rope is improved by 8.6%~67.0%, and the breaking strength is improved by 35.6%~70.4% (Table 3), therefore, the fishing rope breaking load and breaking strength and the fishery safety can be effectively improved by replacing the common fiber ropes in diameters of 8.0mm~10mm in Table 3 with the PP/PE composite monofilament rope ^[1, 10-12]. Similar with other high strength fiber ropes ^[1, 9-20], the elongation disadvantage of PP/PE composite monofilament rope is made up and the demand for impact load of fishing rope is satisfied by the high strength advantage; a greater energy can be absorbed by the PP/PE composite monofilament rope and only a little rebounding force will be generated at rope breaking, the accidental injury to fishers and

farming farm owners caused by rope breaking can be highly reduced, and thus the fishery safety can be highly improved ^[1, 9-20].

Conclusions

The fishing PP/PE composite monofilament was prepared by modification, and the performance-price ratio, safety and tensile mechanical properties of the twisted PP/PE composite monofilament rope were studied in this paper. The result shows the linear density, breaking load, breaking strength and percentage of breaking elongation of PP/PE composite monofilament rope in the diameter of 8.0mm are respectively 32ktex, 9.77kN, 3.05cN/dtex and 18%; if the common fiber rope is replaced by the PP/PE composite monofilament rope without modifying the rope breaking load advantage, the rope diameter can be reduced by 0~20%, the linear density can be reduced by 2.1%~34.7%, the breaking strength can be enhanced by 35.6%~68.5%, the percentage of breaking elongation can be decreased by 61.7%~69.5%, the raw material consumption can be reduced by 2.1%~34.7%, and the netting gear resistance can be reduced correspondingly; safety and tensile mechanical properties are favorable, and there is an extensive prospect of industrialized application.

ACKNOWLEDGEMENT

This research was funded by the Marine Economic Innovation Special Development area

Demonstration Project in Guangdong province "Deep water aquaculture industry engineering

technology research and development of public service platform" (GD2013-D01-001), 2013 Marine

Economic Innovation Demonstration Project "650t Annual Yield of Daiquzu Large Yellow Croaker in Offshore Deep Water Cages", Dongtou Science and Technology Plan "Technological Development for Ecological Marine Farming Barrier High-performance Ropes & Nets in Bailongyu

Island" (N2014K19A), and Taizhou Science and Technology Project "Research and Development

of High Performance Ropes for Deep Water Cages" (14ny17).

REFERENCES

- [1] M. Sun, J. Shi, C. Xu, et al. Fishery material and technology, China agriculture press, Beijing, 2009, PP. 1-138.
- [2] Committee of Teaching Material Compiling for Workers' Skill Training, Ministry of Agriculture. Rope net-making methods and operating skills. Beijing, summary of china agricultural standards. China Press of Standards, Beijing, 1997, PP. 1-160.
- [3] J. Shi, L. Wang, X. Chen, et al. Fishing Netting and Antifouling Technology, China Agriculture Press, Beijing, 2011, PP. 1-446.
- [4] J. Xu. Deep water cages and barrier net aquiculture,: China Agriculture Press, Beijing, 2007, PP. 1-307.
- [5] L. Wang. Experimental research and the fishery application prospect of ultrahigh fibers, Journal of Fisheries of China. 24 (2000) 480-484.
- [6] K. Zhang. Polymer Physics, Chemical Industry Press, Beijing, 1981, pp. 1-213.
- [7] J. Shi, Wenwen Yu, Wenzhu Zhong, et al. Tensile mechanical properties of 3-strand PE/SiO₂ composite fiber rope, Applied Mechanics and Materials, 1033-1034 (2014) 921-926.

- [8] J. Shi, L. Wang, X. Chen, et al. Progress in the research on new synthesized fibers for fisheries. Journal of Modern Fisheries Information, 23 (2008) 9-22.
- [9] H. Ma, Y. Guo, L Mao. Research on the ultrahigh molecular weight polyethylene composite ropes for wind and wave resistant net cage, Marine Fisheries, 27 (2005) 154-158.
- [10] J. Shi, Y. Liu, L. Wang, et al. Research on the physical and mechanical properties of ultrahigh strength ropes for deep water net cages, Modern Fisheries Information, 28 (2013) 127-133.
- [11] J. Shi, L. Wang, X. Chen, et al. Research on the 8-strand high performance polyethylene rope, Journal of Modern Fisheries Information, 11(2010) 17-20.
- [12] J. Shi, Y. Liu, H. Ma, et al. Research on the 4-strand modified PP/PE monofilament rope for fisheries, Journal of Modern Fisheries Information, 12(2010) 16-28.
- [13] Anon. Special rope stronger than steel, Fishing News International, 39 (2000) 34.
- [14] Anon. New polyethylene fiber suitable for deepwater mooring ropes, Offshore, 72 (2012) 90-93.
- [15] Anon. Mocrowaves to dry superstrong ropes, Fishing News International, 39 (2000) 21.
- [16] Anon. Adenia II tows light Dyneema trawl, Fishing News International, 33 (1994) 14.
- [17] Dingzhu Wo. Composite Materials. Chemical Industry Press, Beijing, 2000, pp. 106-113.
- [18] Anon, Fiber developed for long-lasting, deep-water moorings, Advances in Textiles Technology, (2012).
- [19] Y. Guo, H. Ma, L. Mao. Elongation test of fiber rope for net cage, Journal of Fisheries of China, 29 (2005) 724-727.
- [20] J. Shi, L. Wang. Research on the ultrahigh molecular weight polyethylene fiber rope for fisheries, Journal of Shanghai Ocean University, 12 (2003) 371-375.
- [21] GB/T 18674-2002. General technical specifications for ropes for fisheries, China Press of Standards, Beijing, (2002).
- [22] SC/T 5005-2014. Polyethylene Monofilament for fisheries, China Press of Standards, Beijing, (2014).
- [23] GB/T 8834-2006. Ropes Determination of certain physical and mechanical properties, China Press of Standards, Beijing, (2006).
- [24] ISO 1969: 2004. Fiber ropes Polyethylene 3- and 4-strand ropes. Switzerland, (2004).