

The Properties of Epoxy Composites Containing Aligned Iron Oxide Nanorods by Low Magnetic Field

Yu-Ting Li¹, Chuan-Guo Ma^{1,2, a, *}, Qi-Ju Ou¹, Hua-Mei Wan¹, Pei-Bang Dai^{1,2}

¹School of Materials Science and Engineering, Guilin University of Electronic Technology, Guilin, Guangxi, China

²Guangxi Key Laboratory of Information Materials, Guilin, Guangxi, China

^amachuanguo@guet.edu.cn

*Corresponding author

Keywords: Fe₂O₃nanorods, Magnetic Field, Epoxy Resin, Fracture toughness.

Abstract. The magnetic iron oxide (Fe₂O₃) nanorods were synthesized, and the epoxy resin (EP) composites with the content of 1wt% Fe₂O₃ were prepared in the condition of magnetic field. X ray diffraction, scanning electron microscopy and comprehensive physical properties measurement system were used to characterize the composition, morphology and magnetic properties of the nanorods, respectively. The effects of a low magnetic field ($\leq 0.06T$) on fracture toughness, compressive strength and glass transition temperature of the composites were specifically investigated. The results show that the critical stress intensity factor, critical strain energy release rate and the compressive strength of Fe₂O₃/EP composites with magnetic field induction are 1.33 MPa·m^{1/2}, 0.56 KJ/m² and 206.5MPa, which are increased by 7.3%, 27% and 15% compared to of EP effectively.

Introduction

Epoxy resin (EP) is a kind of thermosetting resins with excellent mechanical properties and strong adhesive, which was widely used in the fields of coatings, adhesives, sports, ships, aerospace and others. However, the inherent high cross-linking of EP is easy to cause the brittle fracture of the products, which greatly limits the application of EP. According to the literature [1], the introduction of nanoparticles cause pinning, branching, bridging and deflection of crack, which results in decreasing of the crack driving force at the crack tip, thus plays an important role in improving the fracture toughness of EP. In addition, Khan et al. [2] have indicated that the nanoparticles with large aspect ratio (lamellar, one-dimensional rod like) are favorable for the bridging and deflection of the crack, and the ordered arrangement of the nanorods perpendicular to the direction of crack growth further promotes the crack bridging and deflection. Even though there are many methods to make the orientation of nanoparticles, the magnetic field (MF) induced orientation method is more simple and efficient [3]. Wu et al. [4] have loaded Fe₃O₄ onto graphene nanoplates (GNS) and prepared the GNS - Fe₃O₄/EP composites with and without MF. The results show that when the content of GNS-Fe₃O₄ was 1wt%, the critical energy release rate (G_{IC}) of composites with MF is 819J/m², which is 511% higher than EP and 50% higher than that without MF. Ma et al.[5] have studied the influence of nickel particle-loaded carbon nanotubes (CNTs) on fracture toughness of magnetic nanocomposites with MF. The results show that when CNTs content was 1wt%, the critical stress intensity factor (K_{IC}) and G_{IC} of composites with MF were increased by 49% and 120% compared to EP and increased by 12% and 25% compared to the composites without MF. From the previous literatures, the orientation of lamellar or rod-like particles under MF has to require help of magnetic particles, which makes the process more complicated and inefficient. So far, few studies have been conducted to improve the fracture toughness of EP by one-dimensional magnetic nanoparticles (eg. Fe₂O₃nanorods) with MF induction. The Fe₂O₃nanorods, which were dehydrated by iron oxyhydroxide (FeOOH) particles, not only maintain the rod-like morphology of FeOOH, but also have good magnetic properties to be aligned under a low MF ($\leq 0.1T$). In this work, the Fe₂O₃ nanorods were prepared by two-step method, the Fe₂O₃/EP composites were prepared without MF and with MF. The influence of the aligned

nanorods on the fracture properties, compressive properties and glass transition temperature (T_g) of the composites were investigated when the Fe_2O_3 nanorods content was 1wt%.

Experimental

Materials

Ferrous chloride tetrahydrate ($FeCl_2 \cdot 4H_2O$) and sodium hydroxide (NaOH) were purchased from Xilong chemical Limited by Share Ltd (China). Epoxy resin (diglycidyl ether of bisphenol A, RIMR 135), and curing agent (modified amine, RIMH 134) were supplied by Hexion Specialty Chemicals Inc (USA).

Preparation of Fe_2O_3 /EP Composites

The Fe_2O_3 nanorods were obtained by the two-step method in the literature [6], and the uniform mixture of Fe_2O_3 and EP was obtained by solvent dispersion method. After the mixture and curing agent (30% of EP by weight), were mixed, evenly, in a vacuum oven and then poured into the mold under MF (0.06T) as shown in Fig. 1 and without MF as control. The Fe_2O_3 /EP composites with and without MF can be obtained after cured at 60°C for 12hours. In this study, a single edge notch specimen was fabricated according to ASTM D5045-99 standard.




Figure 1. A schematic representation of preparation of Fe_2O_3 /EP composites under MF .

Characterization

The composition of Fe_2O_3 nanorods was analyzed by X ray diffraction (XRD, model D8-2-Advance, Germany BRUKER). The morphology of Fe_2O_3 nanorods and composite section were investigated using scanning electron microscopy (SEM, model Quanta450FEG, US FEI). The integrated physical properties measurement system (PPMS, model PPMS-9, US Quantum Design) was used to examine the magnetic properties of Fe_2O_3 nanorods at room temperature. The mechanical properties of composites were measured on the universal material testing machine (WDW-E100, Ji'nan Shijin Group Co. Ltd.) with a crosshead speed of 1.0mm/min. The specimens for compression test were prepared according to GBT2567-2008. K_{IC} was determined using a single edge notch bend (SENB) test according to ASTM D5045-99 standard and the modified SENB specimens [5]. The T_g of composite materials was tested by differential scanning calorimetry (DSC, DSC204, NETZSCH) at the temperature range of -40 to 200°C and with a heating rate of 10K/min.

Results and Discussion

Characterization of Fe_2O_3 Nanorods

Fig.2 (a) is the XRD pattern of Fe_2O_3 nanorods. According to the XRD data analysis software (Jade 6.5), the diffraction peaks at 45.62 °, 51.43 °, 60.64 °, 77.72 ° and 84.75 ° correspond to the crystal plane (400), (511), (440) of the standard Fe_2O_3 (PDF # 39-1346) respectively. In addition, the other peaks are not observed in the pattern, which reveals that the product is pure Fe_2O_3 . As shown in Fig. 2 (b), Fe_2O_3 has a one-dimensional rod shape, the length is about 0.6 μm and the

diameter is about 50nm, all of nanorods are uniform. Fig. 2 (c) and (d) show the magnetic properties of Fe₂O₃nanorods. It can be seen from the Fig. (c), the Fe₂O₃nanorods show a high saturation magnetization of 38.06 emu/g and paramagnetism. Fig. 2 (d) is the SEM image of Fe₂O₃ dispersed in alcohol and induced by MF. It can be found that not only the aggregated nanorods but also the single Fe₂O₃ is aligned along the direction of the magnetic field. This indicates that the induction of MF could lead the Fe₂O₃nanorods to be oriented.





Figure 2. Characterization of Fe₂O₃nanorods. (a) XRD pattern, (b) SEM image without MF induction, (c) hysteresis loop and (d) SEM image with MF induction .

Characterization of Fe₂O₃/EP Composites

Fracture Toughness

Table 1. Mechanical properties of composites.

Materials	K _{1C} (MPa·m ^{1/2})	G _{1C} (KJ/m ²)	Compressive strength (MPa)
EP	1.24	0.44	179
Fe ₂ O ₃ /EP without MF	1.04	0.31	207.5
Fe ₂ O ₃ /EP with MF	1.33	0.56	206.5






Figure3. Fracture morphology of composites. (a) EP, (b) Fe₂O₃ /EP composites without MF and (c) Fe₂O₃ /EP composites with MF.

Table 1 shows the fracture toughness of the composites with MF and without MF by K_{IC} and G_{IC} . From the data, it can be seen that the K_{IC} and G_{IC} of the composites without MF are $1.04 \text{ MPa}\cdot\text{m}^{1/2}$ and 0.31 KJ/m^2 , which are lower than those of the pure EP at $1.24 \text{ MPa}\cdot\text{m}^{1/2}$ and 0.44 KJ/m^2 . Whereas, the K_{IC} and G_{IC} of the composites with MF are $1.33 \text{ MPa}\cdot\text{m}^{1/2}$ and 0.56 KJ/m^2 , which are 7.3% and 27% higher than that of pure EP, respectively. In terms of the improvement in K_{IC} and G_{IC} compared to that of the pure EP, the results is not particularly significant compared to the reported results. Tao et al.[7] reported that the K_{IC} of the composites is lower than that of pure EP when adding the same amount of Fe₂O₃ particles in the EP, which is similar to that of the composites without MF. However the percentage of increase in K_{IC} and G_{IC} of the composites with MF is lower than that in the work[5]. It may be mainly attributed to the poor dispersion of the nanorods in the composites and weak interface interaction between the nanorods and the EP, which are shown in the next fracture surface morphology analysis. But it is noted that the K_{IC} and G_{IC} of the composites with MF are 27.9% and 80.6% higher than that of the composites without MF, respectively. This indicates that the effect of MF on the properties of the composites is very significant even compared with the reported results [5].

In order to further explain the toughening effect of Fe₂O₃nanorods on EP, the fracture surface morphology of composites was analyzed by SEM. Fig. 3 (a) is the fracture surface of pure EP, which can be seen that the crack tip is smooth and without any other material. The fracture surface of the composites without MF shown in Fig. 3 (b), as can be seen that at the beginning of the crack has obvious nanoparticles and voids, which is due to the broken nanorods and pull out of nanorods when the composites broken. The behaviors of the nanorods could have led the energy to dissipate and play a role in improving the fracture properties of EP. Unfortunately, due to the interface defects between nanoparticles and EP, and the randomly dispersed nanoparticles in the composite without MF, the fracture of composites caused much more debonding of nanorods rather than the broken nanorods and pull-out of nanorods, does not achieve the purpose of toughening. This mechanism is illustrated in Fig. 4 (a). Fig. 3 (c) is the fracture surface of the composites with MF, which can be clearly seen that there are broken traces of the nanorods. With the help of MF induction, the nanorods are arranged perpendicular to the crack growth direction, and formed a continuous acicular network in EP. Under the action of stress, the crack has to pass all nanorods to break the composites as shown in Fig. 4 (b). The process is accompanied by more broken nanorods and pull out of nanorods. In addition, there is enough power to make the crack deflected or terminated, so as to improve the fracture toughness of EP. The toughening mechanism is the same as that proposed in the literature [1].




Figure 4. Schematic diagram of Fe₂O₃ nanorods toughening EP. (a) Without MF and (b) with MF.

Compression Property and T_g of Composites




Figure 5. T_g of pure EP and the composites with and without MF

When the material is subjected to stress, besides the fracture failure, often accompanied by compression failure. As can be seen from Table 1, the compressive strength of Fe₂O₃/EP composites without MF is 207.5MPa, which is 15.9% higher than that of pure EP. The compressive strength of composites with MF is 206.5MPa, which is 15.4% higher than that of EP. Obviously, the addition of nanorods could improve the compressive properties of EP. In this work, the direction of the magnetic field is parallel to the direction of the compressive stress, which makes the rod-like particles parallel to the stress direction. Thus with the condition of the same load, the nanorods with MF are easier to be damaged than those without MF, so the compressive strength of composites without MF is slightly higher than that with MF.

The T_g of Fe₂O₃/EP composites were investigated by DSC. It is shown in Fig. 5 that the T_g of pure EP and Fe₂O₃/EP composites without MF and with MF are 101.2°C, 104.3°C and 102.3°C, respectively. There are a lot of factors affecting the T_g of composites. In the composites the introduction of Fe₂O₃, which hindered the movement of the EP molecule segment, makes the T_g of EP increased. From Fig. 2 (d), it can be seen that the Fe₂O₃ nanorods are easy to be gathered in the condition of MF. There may be a vacancy in the vicinity of the oriented nanorods, which cannot more efficiently restrict EP molecule segment compared to the randomly dispersed Fe₂O₃ nanorods without MF. So the T_g of Fe₂O₃/EP composites without MF is higher than that with MF.

Conclusions

The magnetic Fe₂O₃ nanorods were successfully synthesized through two-step method and can be aligned along the direction of the magnetic field. In addition, the Fe₂O₃/EP composites without MF and with MF were prepared when the content of Fe₂O₃ nanorods was 1wt%. The effects of MF on fracture toughness, compressive strength and T_g of the composites were compared with pure EP, respectively. Although the toughening effect is not particularly significant compared to the other

works, the fracture toughness of Fe₂O₃/EP composites with MF is much higher than the composites without MF. It is revealed that the aligned Fe₂O₃ nanorods can improve the fracture properties of EP effectively using a low MF. Furthermore, due to the addition of Fe₂O₃ nanorods, the compressive strength and T_g of EP have been increased to a certain degree, no matter in the condition of MF or without MF.

Acknowledgements

The authors gratefully acknowledge the supports from the National Natural Science Foundation of China (Grant #51363003), and the Guangxi Natural Science Foundation(2016JJA160040).

References

- [1] H.Y. Liu, G.T. Wang, Y.W. Mai, On fracture toughness of nano-particle modified epoxy, *J. Composites Part B Engineering*, 42 (2011) 2170-2175.
- [2] S.U. Khan, J.R. Pothnis, J.K. Kim, Effects of carbon nanotube alignment on electrical and mechanical properties of epoxy nanocomposites, *J. Composites Part A Applied Science & Manufacturing*, 49 (2013) 26–34.
- [3] S. Wu, R.B. Ladani, J. Zhang, Aligning multilayer graphene flakes with an external electric field to improve multifunctional properties of epoxy nanocomposites, *J. Carbon*, 94 (2015) 607-618.
- [4] S. Wu, J. Zhang, R.B. Ladani, A novel route for tethering graphene with iron oxide and its magnetic field alignment in polymer nanocomposites, *J. Polymer*, 97 (2016) 273-284.
- [5] C. Ma, H.Y. Liu, X. Du, Fracture resistance, thermal and electrical properties of epoxy composites containing aligned carbon nanotubes by low magnetic field, *J. Composites Science & Technology*, 114 (2015) 126-135.
- [6] C. Sudakar, G.N. Subbanna, T.R.N. Kutty, Effect of anions on the phase stability of γ -FeOOH nanoparticles and the magnetic properties of gamma-ferric oxide derived from lepidocrocite, *J. Journal of Physics & Chemistry of Solids*, 64 (2003) 2337-2349.
- [7] T. Sun, H. Fan, Z. Wang, X. Liu, Z. Wu, Modified nano Fe₂O₃-epoxy composite with enhanced mechanical properties, *J. Materials & Design*, 87 (2015) 10-16.